

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Withdrawn) A white light emitting diode comprising a phosphor layer to convert blue light into yellow light, provided on a blue light emitting diode,

wherein the phosphor layer comprises an inorganic compound containing a phosphor

wherein the phosphor is (Y, Gd, Ce)₃Al₅O₁₂, an oxide phosphor in which Zn, Ca, Mg, Sr, Sm or Ga is added into (Y, Gd, Pr)AlO₁₂ or (Y, Gd, Ce)Al₅O₁₂, a phosphor in which CaS, Ga₂S₃ or EuS is mixed to be calcined, or a phosphor in which divalent Eu is activated to α -SiALON.

2. **(Withdrawn)** The white light emitting diode of claim 1,
wherein the inorganic compound is the phosphor.
3. **(Withdrawn)** The white light emitting diode of claim 1,
wherein the inorganic compound comprises a transparent
inorganic oxide.
4. **(Withdrawn)** The white light emitting diode of claim 3,
wherein the transparent inorganic oxide is an oxide of at
least one kind selected from Al, Si, Ti, Ge, P, B, Y, Sn, Pb, Gd,
Lu, Sc, In, Mg, Ca, Sr and Ba.
5. **(Withdrawn)** The white light emitting diode of claim 3,
wherein the transparent inorganic oxide is silica or
alumina.
6. **(Currently amended)** A method of manufacturing a white light
emitting diode comprising a phosphor layer to convert blue light
into yellow light, provided on a blue light emitting diode, the
method comprising a step of forming the phosphor layer comprising

an inorganic compound containing a phosphor via an aerosol deposition method by which particles are deposited on a substrate via collision of the particles with a surface of the substrate in a vacuum.

7. (Original) The method of claim 6,

wherein a compound as the phosphor being the inorganic compound is prepared.

8. (Original) The method of claim 6,

wherein the inorganic compound comprising a transparent inorganic oxide is prepared.

9. (Currently amended) The method of claim ~~[[6]]~~ 8,

wherein an oxide of at least one kind selected from Al, Si, Ti, Ge, P, B, Y, Sn, Pb, Gd, Lu, Sc, In, Mg, Ca, Sr and Ba as the transparent inorganic oxide is prepared.

10. (Currently amended) The method of claim ~~[[6]]~~ 9,

wherein the transparent inorganic oxide being silica or alumina is prepared.

11. (New) The method of Claim 6 wherein the film formation rate is 10-30 $\mu\text{m}/\text{min}$.